



The Forge, Innishannon
 County Cork, Ireland
 TEL: +353 (0)21 4776677
 FAX: +353 (0)21 4776063
 TECHNICAL HELPLINE IRL / INT: +35 321 4776677
 TECHNICAL HELPLINE UK: +44 1737 245554
info@roundtowerlime.com
<http://www.roundtowerlime.com/>

HYDRAULIC LIME MIXES

Application		Roundtower	Typical Mix	Approx. Coverage (Per 25kg Bag)
Internal Plastering	Backing Coats (10mm)	NHL2	2.5 Sand: 1 Lime	8m ²
	Finishing Coat (3mm)	NHL2	2 Fine Silica sand: 1 Lime	26.5m ²
External Rendering	Coat (10mm)	NHL2	2.5 Sand: 1 Lime	8m ²
		NHL3.5	2.5 Sand: 1 Lime	8m ²
Pointing Rubble Stone		NHL2	2.5 Sand: 1 Lime	10m ²
Pointing Brickwork		NHL2	2.5 Sand: 1 Lime	16m ²
		NHL3.5	2.5 Sand: 1 Lime	16m ²
Harling/Wet Dash/Roughcast		NHL3.5	2.5 Sand /Aggregate: 1 Lime	7.5m ²
Slurry Coats		NHL2	2.5 Sand: 1 Lime	Refer to supplier
		NHL3.5	2.5 Sand: 1 Lime	Refer to supplier
Lime Concrete		NHL5	1.5 Mixed Aggregate: 1 Lime	Refer to supplier

WE ALSO RECOMMEND THE USE OF NHL5 IN AREAS OF HIGH EXPOSURE (E.G. MARINE CONDITIONS)