

Skamol Lime Mortar

	Value	Unit
Mixing ratio		
Hydrated lime	35	kg
Hydraulic lime (NHL)	65	kg
Quartz sand	499	kg
Natural latex	<1	%
Characteristics		
Chloride content	<0.1	%
Thermal conductivity (table value)	0.90	W/mK
Durability against frost/thaw	MX1 to MX4	
General		
Bag size	20	kg
Consumption, 7mm (per bag)	2.5	m ²
Shelf life	24	months
Pouring temperature	+5 to +25	°C
Opening time at +20°C	60	minutes
Added water (per bag)	4.5	L
Classification reaction to fire (EN 13501-1:2007 + A1:2009)	Class A1	
HS Tariff number (Harmonized Commodity Description and Coding System)	3824.50.90	
Colour	Off-white	



Data are average results of tests conducted under standard procedures and are subject to variation. Data contained in this data sheet are supplied in good faith as a technical service and are subject to change without notice. Misprint and errors excepted. Revision number: 2.10.2023