

Technical Data

GLAPOR Insulation gravel SG 800 E



characterization:

Factory made cellular glass loose fill according to EAD 040394-00-1201

application areas:

load bearing and thermal insulation layer underneath floor slabs
a thermal insulation/frost protection layer in areas with in-ground frost (also in road construction)
lightweight fill

characteristics: general		perform.	dimension	specification / value
product / material / composition		100	%	high-quality recycled glass
colour		grey		
characteristics: Europe		perform.	dimension	specification / value
compressive stress $f_{1,3 : 1 + \text{deformation} = 10 \%}$		≥ 800	kPa	EN 826
particle size *		32 - 63	mm	EN 933-1
loose bulk density ** dry		150 - 170	kg/m ³	EN 1097-3
thermal conductivity $\lambda_{D \text{ dry}}$		0,085	W/mK	EN 12667
thermal conductivity $\lambda_{D \text{ moist (correction factor 1,2)}}$		0,102	W/mK	ETA-20/0192
oedometer modulus $E_{OED} \text{ (load level: 500 kPa)}$		≈ 7360	kPa	ETA-20/0192
creep strain compression (load level: 250 kPa)		not specified	%	ETA-20/0192
brand behavior		A 1	Klasse	EN 13501
characteristics: national		perform.	dimension	specification / value
shear parameter	cohesion c	$\approx 53,1$	kN/m ²	german: DIN 18137-3
	friction angle ϕ	$\approx 41,2$	°	german: DIN 18137-3
	Nominal shear stress (load level: 250 kN/m ²)	$\approx 274,9$	kN/m ²	german: DIN 18137-3
coefficient of permeability		$\approx 3,8 \cdot 10^{-4}$	m/s	german: DIN 18130-1, Ann. B
further characteristics		perform.	dimension	specification / value
stiffness modulus Es		13000	kPa	german: abZ/aBg Z-23.34-1778
buoyancy (1,3 : 1 compressed)		$\approx 1,4$	kN	
resisting horizontal forces		30	%	according normal stress
capillary-breaking		yes		
health / fire protection / finishing		perform.	dimension	specification / value
compression factor load bearing		1,3 : 1	Vol.-%	ETA-20/0192
min. installation thickness load bearing (1,3 : 1 compressed)		≥ 150	mm	german: abZ/aBg Z-23.34-1778
max. installation thickness load bearing (1,3 : 1 compressed)		≤ 900	mm	german: abZ/aBg Z-23.34-1778
delivery format / Package				
loose form / loose form at bulk material cloth				
Big Bag:		1,5 m ³	3,0 m ³	

* The specification of the grain size refers to $\geq 75\%$ of all grains; according to the standard, oversize (max. 10% up to twice the grain size) and undersize can be included.

** The insulation gravel may contain moisture due to storage and installation.

This information corresponds to the state of knowledge at the time of printing. Subject to errors and changes without prior notice.

Newer editions replace older versions. Current versions can be found in the download area of our website.

© The content of our data sheets, especially the layout, is protected by copyright. The copyright lies with GLAPOR WERK Mitterteich GmbH.

In the event of different information in translated data sheets, the German version is always decisive.

Issue date: 10. Januar 2025

GLAPOR Werk Mitterteich GmbH

Hüblteichstraße 17
95666 Mitterteich
Germany

Tel.: +49 (0) 96 33 40 07 69 - 0
Fax: +49 (0) 96 33 40 07 69 - 19
Mail: info@glapor.de



www.glapor.de